


SNSH-C22 Hex Socket Head Cap Screws (Hastelloy C - 22 equiv.)







Chemical-proof

Mechanical property

	Hastelloy (UNS N06022)	SUS304
Tensile Strength (N/mm²)	786	520 or Higher
0.2% Proof Stress (N/mm²)	365	205 or Higher
Elongation (%)	57	40 or Higher
Hardness (HRB)	92	90 or Less

• Values in chart are for reference only. They are not guaranteed values.

Physical property

	Hastelloy (UNS N06022)	SUS304
Specific Gravity	8.61	7.93
Longitudinal Elastic Modulus (GPa)	209	193
Specific Heat (J/kg·K)	381	500
Electric Resistance ($\mu\Omega \cdot m$)	1.2	0.7
Linear Expansion Coefficient (K-1)	12.4 x 10 ⁻⁶	17.3 x 10 ⁻⁶

• Values in chart are for reference only. They are not guaranteed values.



- Hastelloy C-22 is one of the few metals that is resistant to wet chlorine gas, hypochlorite, and chlorine dioxide.
- Excellent corrosion resistance against oxidizing and reducing acids and salts. → P.xxxx
- For aquatic applications that use sea and salt water.
- Cleanroom wash and cleanroom packing are completed. → P.xxxx

Application

FPD production equipment, semiconductor devices, printed circuit board etching devices, metallic surface treatment equipment and facilities, and chemical plants

Material/Finish

RoHS	

	SNSH-C22
Main Body	UNS N06022(Hastelloy*1C-22 equiv.)

*1: Hastelloy is a registered trademark of Haynes International,

Unit:mm

	M (Coarse)											D1	L1		Tension*1	
Part Number	Nominal of Thread 1	Pitch	L (2)												Rupture Load Mass (g) (N)	
SNSH-M3-C22	M3	0.5	6	8	10	12	16	20				5.5	3	2.5	3950	0.79 - 1.5
SNSH-M4-C22	M4	0.7		8	10	12	16	20	25			7	4	3	6900	1.8 - 3.5
SNSH-M5-C22	M5	8.0			10	12	16	20	25			8.5	5	4	11100	3 - 5.3
SNSH-M6-C22	M6	1				12	16	20	25	30		10	6	5	15700	5.6 - 9.2
SNSH-M8-C22	M8	1.25					16	20	25	30	35	13	8	6	28700	13 - 21

*1: Values in chart are for reference only. They are not guaranteed values.

• Part number specification



Batch cleanroom packing is provided for orders containing multiple items of the same size.



