


Plastic Screw PVDF / Hex Head Screws







Application

FPD production equipment / Semiconductor devices / Printed circuit board etching devices / Metallic surface treatment equipment and facilities / Chemical plants / Food industry machines

Material/Finish	∅ RoHS
	SPV-H
Main body	PVDF (Polyvinylidene Fluoride) (Milky White)
Heat resistance temperature*1	150℃

*1: This is the value for the plastic material. The maximum operating temperature of the product changes with performance conditions such as tightening torque.



- PVDF has excellent corrosion resistance against strong acids and organic solvents as well as halogen compounds such as hydrogen sulfide and bromine.
- It can be used in atmospheres in which metal and PVC (polyvinyl chloride) cannot be used.
- Max. Operating Temperature*1 (min./max.): 40/150℃
- Its tensile strength equals or exceeds PVC, and its impact strength is 3 times that of PVC.
- It is self-extinguishing and has excellent incombustibility.
- The properties and precautions of plastic screws → P.xxxx

Unit:mm

Part Number	M (Coarse)												Tension*1	Torsional*1		
	Nominal of Thread 1	Pitch	L 2								В	L1	Rupture Load (N)		Mass (g)	Qty per pack
SPV-M4-H	M4	0.7	10		15	20	25				7	2.8	429	0.26	0.39 - 0.71	20
SPV-M5-H	M5	0.8	10	12	15	20	25	30	35		8	3.5	688	0.44	0.64 - 1.5	20
SPV-M6-H	M6	1	10	12	15	20	25	30	35	40	10	4	960	0.81	1 - 2.5	10
SPV-M8-H	M8	1.25	10	12	15	20	25	30	35	40	13	5.5	1803	1.56	2.2 - 4.7	10
SPV-M10-H	M10	1.5			15	20	25	30	35	40	17	7	2824	3.16	4.9 - 8.2	10
SPV-M12-H	M12	1.75				20	25	30	35	40	19	8	4249	5.73	7.9 - 12	10

- *1: Values in chart are for reference only. They are not guaranteed values. The recommendation torque is 50% of the torsional torque.
- When purchasing less volume than one full bag, a separate handling fee is charged. For details, see the Sold Separately Service.

• Part number specification





